

BOQ

| ITEM NO | DESCRIPTION OF THE ITEMS | UNIT |
|---------|---|------|
| 1.0 | Epoxy resin based ESD self-smoothing floor toppings at 2.0mm thk | sqm |
| 1.1 | Epoxy resin based ESD self-smoothing floor toppings: Nitoflor Conductive system | |
| a. | <p>Surface preparation: All floors to receive Nitoflor SL Conductive topping should be protected by means of a damp-proof membrane. The absence of such membranes could lead to the problem of osmosis/rising dampness where soluble salts have concentrated.</p> <p>New concrete or cementitious substrates should have been placed at least 28 days earlier and have moisture content of less than 5% before topping with Nitoflor SL Conductive system. This can be checked by using a Thermo Hygrometer. With non-self-supporting concrete floors transfer of moisture from the soil might occur, resulting in adhesion failures of the flooring system.</p> <p>The long term durability of the applied Nitoflor SL Conductive is dependent upon the adhesive bond achieved between the flooring material and substrate. It is most important therefore, that substrate surfaces are correctly prepared prior to application.</p> <p>All substrates should be sound and free from contamination such as mortar and paint splashes, curing Compound residue, oil or grease. Excessive laitance should be removed by light mechanical scabbling, grinding or grit blasting</p> | |
| b. | <p>Priming: Prepared substrates to be treated with Nitoflor SL Conductive system should be primed with Nitoprime 25*. Should be mixed in the proportions supplied by adding the entire contents of hardener can to the base can. Once mixed the Nitoprime 25 primer, should be immediately applied in a thin, continuous film using stiff brushes or rollers. Over application and puddles should be avoided. Porous floors may require two coats of Nitoprime 25. Nitoprime 25 should be allowed to become tack free prior to application of Nitoflor SL Conductive Undercoat.</p> | |
| | <p>Epoxy Conductive Topping: providing mixing and laying The areas indicated shall be applied with an epoxy resin based static Conductive Nitoflor SL Conductive floor topping, which shall provide an effective charge dissipation to the earth when applied over concrete or steel substrates. static Conductive areas (Resistance 25×10^3 to 1×10^6 Ohms) When measured for surface resistance in accordance with ASTM F150, the static Conductive topping including Under coat shall be in the range of $25 \times 10^3 - 1 \times 10^6$ Ohms. The surface resistance of the Conductive undercoat shall be in the range of $3 \times 10^3 - 9 \times 10^3$ Ohms. shall have the following property CS (BS 6319) 50N/mm², TS : 16N/mm²,FS:34N/mm² SELF ADHESIVE COPPER TAPE of 100microns thickness and 25mm in width shall be positioned in a grid form 10.0M C/C in both directions, well connected to a Earthing point provision shall be made for every 300 sqm one Earthing point .Cost Inclusive of Supply ,apply,Equipments. Exclusive of GST as applicable,. Client shall provide Storage, Power, water, etc. Flooring work shall be executed by Fosroc Authorised Applicator.</p> | |
| 1.2 | Epoxy resin based ESD self-smoothing floor toppings: Nitoflor Dissipative system | |



| | | |
|-----|--|-----|
| a. | <p>Surface preparation: All floors to receive Nitoflor SL Dissipative topping should be protected by means of a damp-proof membrane. The absence of such membranes could lead to the problem of osmosis/rising dampness where soluble salts have concentrated.</p> <p>New concrete or cementitious substrates should have been placed at least 28 days earlier and have moisture content of less than 5% before topping with Nitoflor SL Dissipative system. This can be checked by using a Thermo Hygrometer. With non-self-supporting concrete floors transfer of moisture from the soil might occur, resulting in adhesion failures of the flooring system.</p> <p>The long term durability of the applied Nitoflor SL Dissipative is dependent upon the adhesive bond achieved between the flooring material and substrate. It is most important therefore, that substrate surfaces are correctly prepared prior to application. All substrates should be sound and free from contamination such as mortar and paint splashes, curing Compound residue, oil or grease. Excessive laitance should be removed by light mechanical scabbling, grinding or grit blasting</p> | |
| b. | <p>Epoxy Dissipative Topping: providing mixing and laying The areas indicated shall be applied with an epoxy resin based static Dissipative Nitoflor SL Dissipative floor topping, which shall provide an effective charge dissipation to the earth when applied over concrete or steel substrates. Static Dissipative areas (Resistance 10^6 to 10^9 Ohms) The surface resistance of the Dissipative undercoat shall be in the range of 3×10^4 - 8×10^4 Ohms. When measured for surface resistance in accordance with ASTM F150, the static Dissipative topping including undercoat shall be in the range of 1×10^6 - 1×10^9 Ohms. shall have the following property CS (BS 6319) 50N/mm², TS : 16N/mm²,FS:34N/mm² SELF ADHESIVE COPPER TAPE of 100microns thickness and 25mm in width shall be positioned in a grid form 10.0M C/C in both directions, well connected to a Earthing point provision shall be made for every 300 sqm one Earthing point .Cost Inclusive of Supply ,apply,Equipments. Exclusive of GST as applicable,. Client shall provide Storage, Power, water, etc. Flooring work shall be executed by Fosroc Authorised Applicator.</p> | |
| 1.3 | <p>PU floor Coving: Nitoflor Coving UT size - 75mm x 75mm</p> | rmt |
| a. | <p>Surface Preparation: Removing all laitance and any surface sealer or curing membrane by mechanical means such as shot-blasting, grinding or light scabbling to the level of sound concrete. After surface preparation, all loose debris and dirt should be removed by vacuum equipment.</p> | |
| b. | <p>Priming: Priming is carried out using a mix of Part A and Part B only. Thoroughly drain the contents of the hardener component into the base component and mix for a minimum of 1 minute or to provide a homogeneous mix. Apply by roller or brush and spread uniformly at the rate of approximately 5m²/1kg set depending on the substrate. Nitoflor Coving UT must be applied wet to wet onto the primed surface before the primer is cured</p> | |
| c. | <p>Polyurethane coving mortar: Providing and applying 3 components, Water based Polyurethane coving mortar Nitoflor Coving UT topped with a sealer coat Nitoflor HB 200UT of Fosroc make. The substrate shall be prepared properly prior laying UT coving, priming the surface with suitable primer as recommended in the manufacturer datasheet @ 12.5m²/2.5kg set depending on the substrate. Laying Nitoflor Coving UT 1.8 - 2.0 kg/m²/mm thickness wet to wet onto the primed surface before the primer is</p> | |

| | | |
|-----|--|-----|
| | cured. Followed by applying 3 components Water-based high-build polyurethane coating sealer coat Nitoflor HB 200 UT in 2 coats 6 m ² per 4.75 kg pack per coat@ 200microns WFT per coat. Fosroc Nitoflor HB200 UT is available in a range of standard Fosroc colours. Complete as per the manufacturer Instruction. | |
| 1.4 | Expansion joints | rmt |
| a. | Surface preparation: Clean the surface and remove any dust, unsound or contaminated material, plaster, oil, paint, grease, corrosion deposits or algae, Oil and grease deposits should be removed by mechanical means. | |
| b. | Priming: Prime sealing slot surfaces with Primer No. 20 using a clean dry brush. Colpor 200 must be applied between 30 minutes and 2 hours after priming. | |
| c. | <p>PU Sealant: Providing mixing and laying PU Sealant at the designated joints are to be sealed using Fosroc Colpor 200PF over the Backer rod of Expancel which shall position on the filler board of Hydrocel XL of the Expansion joint , pavement sealant manufactured by Fosroc to BS 5212: 1990 and U.S.Federal Specification SS-S 200E:1984.. Colpor 200PF has a movement accommodation factor of 30% in butt joints.. To ensure the sealant operates within its stated movement capacity of 30%, the width of sealing slots should be designed in accordance with the recommendations of IRC-57-2006. In trafficked areas the expansion joint width should not generally Exceed 30 mm.</p> <p>Joint depth: In trafficked areas the sealing slots should be constructed so that at no time during the anticipated operating cycle of the joint will the sealant protrude above the surface of the concrete pavement. It is necessary to recess the level of the sealant 5 to 8 mm below the pavement surface, dependent on the time of year and temperature prevailing at the time of sealing.</p> <p>Note: The width to depth ratio of the Colpor 200PF seal should be 1:1 to 1½:1 subject to a minimum 10 mm depth of sealant (example, contraction joint: 15 mm wide x 13 mm depth; expansion joint: 25 mm wide x 20 mm depth). Complete as per the manufacturer Instruction. Cost Inclusive of Supply, apply, Equipment's. Exclusive of GST as applicable. Client shall provide Storage, Power, water, etc. Flooring work shall be executed by Fosroc Authorised Applicator.</p> | |