



Fosroc Nitoflor SL3000 UT

Flow applied medium to heavy duty cementitious polyurethane floor topping

Description

Nitoflor SL3000 UT is a medium-heavy duty, flow applied cementitious polyurethane floor topping system designed with the highest order of durability to resist abrasion, chemical attack and other physical aggression.

Typical application areas include food and beverage production, dairy processing, pharmaceutical and engineering process areas.

Appearance

Smooth matt finish.

Advantages

- Ease of application
- Non Taint
- Easy to clean
- Seamless
- Tough, high resistance to damage

Thickness

3 – 6 mm

Chemical Resistance

Nitoflor SL3000 UT is resistant to a wide range of commonly used chemicals in the food, dairy and pharmaceutical industries, and engineering workshops. Good housekeeping practices should be employed. Please consult Fosroc for further advice.

Substrates

Concrete, polymer modified screeds, grano concrete.

Typical Properties (Tolerance 10%)

BS 8204-6 (3 mm)	Type 5 Floor (medium duty)
BS 8204-6 (4-6mm)	Type 7 Floor (heavy duty)
Compressive Strength,	
ASTM C109, 28 days, MPa	45
BS6319-2, 28 days, MPa	50
Tensile Strength,	
BS6319-7, MPa	7
Flexural Strength,	
BS6319-3, MPa	15
Density	
(ASTM D792), kg/ m ³	1945
Dynamic elastic modulus	
(ASTM C597), MPa	6500
Flexural Modulus	
(ASTM C580), MPa	3200
Taber abrasion resistance	
(ASTM D4060)	
H22 wheels, mg/1000 cycles	143
CS17 wheels, mg/1000 cycles	120
Water absorption	
(ASTM C413) %	0.01
Thermal Expansion Coefficient	
(BS EN1770), /°C	6.1 x 10 ⁻⁵
Impact Resistance	
(ASTM D2794), Joules	
6mm thickness	16
Thermal conductivity	
(Thermtest TPS method), W/m.K	0.1132
Cleanability	Pass
Non-taint property	
(IS-8639, 24 hours)	Pass
Service Temperature 3-4mm	-5°C to +60°C
Service Temperature 6mm	-10°C to +90°C
Ideal application temperature	
range, °C	15 - 30

Note: The typical physical properties given above are derived from testing in a controlled laboratory environment. Results derived from testing field-applied samples may vary, dependent on actual site conditions.

The slip resistance figures given above are affected by application techniques and prevailing site conditions. Slip resistance can reduce over time due to poor maintenance, general wear or surface contaminants. Nitoflor SL3000 UT has a smooth finish so can be expected to become slippery when wet. Good housekeeping practices must be observed.

Fosroc Nitoflor SL3000 UT

Chemical Resistance Chart

ASTM D 1308, Temperature : 25 °C

Chemical	24hr Exposure Result
Hydrochloric Acid Solution (10%)	R
Sulphuric Acid Solution (20%)	R
Ethylene Glycol	R
Acetone	R
Brake Fluid	R
Castor Oil	R
Coconut Oil	R
Grape Juice	R
Diesel Oil	R
Ethanol	R
Iso-Propanol	R
Kerosene	R
Lactic Acid	R
Lime Juice	R
Milk	R
Phosphoric Acid (50%)	R
Skydrol	R
Sodium Bicarbonate (Saturated)	R
Sodium Hydroxide (50%)	R
Sodium Hypochlorite (15%)	R
Vegetable Oil	R
White Spirit	R
Xylene	R
Olive Oil	R

Legend:

R : Resistant, No sign of changing colour, cracking, blistering and disintegration were observed

Cure Schedule at 30°C

Working life of full packs:

Nitoflor SL3000 UT	15 - 20 minutes
--------------------	-----------------

Note: Usable working life of material following mixing and immediate spreading as per the application instructions

Finished floor:

Cure time to light pedestrian traffic	12 hours
---------------------------------------	----------

Cure time to light wheeled traffic	24 hours
------------------------------------	----------

Cure time to medium duty traffic	48 hours
----------------------------------	----------

Cure time to heavy duty traffic	7 days
---------------------------------	--------

Full chemical resistance	7 days
--------------------------	--------

Note: The above cure times are approximate and given as a guide only. These times can vary due to prevailing site conditions and temperature.

Instructions For Preparation And Use

Fosroc Nitoflor SL3000 UT should be installed by specialist applicators, who must follow the procedures laid down in guideline documents such as BS 8204 Part 6:2008 Code of practice – Synthetic Resin Floorings, and the Fosroc Method Statement - PU Cementitious Flooring.

Application Conditions

Ideal ambient, material and substrate temperature range is 15 - 30°C to achieve best results. The product components should be stored in a cool area (or warm area in the case of low ambient temperature), using localised forced cooling or heating equipment as appropriate, in order to bring product temperature within the ideal range. The product can be applied outside this ideal temperature range (subject to a minimum of 10°C and maximum of 34°C) however the surface finish may be subject to spike roller marks. In these cases physical properties and durability of the floor are not affected.

The substrate and applied floor must be kept at least 3°C above the dew point to reduce the risk of condensation or blooming on the surface, from before priming to at least 48 hours after application of Nitoflor SL3000 UT.

Surface Preparation

Inadequate preparation may lead to loss of adhesion and failure. With flow-applied systems, there is a tendency for the finish to mirror imperfections in the substrate. Grinding or light vacuum-contained shot-blasting is therefore preferred over planing for these systems. Percussive scabbling or acid etching is not recommended.

Anchorage grooves must be cut to a minimum depth and width of 2x the flooring thickness to be laid: at the edges or perimeter; day joints; up-stands; drains; doorways and at regular points across the floor, and all debris removed.

New concrete floors

The base should be a minimum of Grade RC30 of BS 8500-2: 2002 and should not contain a water repellent admixture. The surface strength when assessed using a rebound hammer should be above 25 or the surface tensile strength should exceed 1.5 MPa.

The laitance and any surface sealer or curing membrane should be removed by mechanical means such as shot-blasting or grinding to expose the coarse aggregate. After surface preparation, all loose debris and dirt should be removed by vacuum equipment.

For concrete bases in contact with the ground, a damp-proof membrane should have been incorporated into the slab design, in accordance with the requirements of CP102 (Code of practice for the Protection Of Buildings Against Water From The Ground).



Fosroc Nitoflor SL3000 UT

Old concrete floors

All laitance and surface contamination should be removed by mechanical means such as shot-blasting or grinding to expose the coarse aggregate. After surface preparation, all loose debris and dirt should be removed by vacuum. Heavy oil or grease deposits should be removed either mechanically, or by steam cleaning, or by biological treatment, then by high pressure water blasting followed by the application of a penetrating primer. Where oil or grease contamination has been severe or of long duration, these methods may prove unsatisfactory and in these cases removal of the affected base is necessary.

In existing buildings without a functioning damp-proof membrane, the application of a surface-applied membrane should be considered. Hydrostatic pressure may, under certain circumstances, cause adhesive failure between the flooring and the substrate. Where this is likely to occur, such as in areas where the ground water table is higher than the substrate, and where external tanking has not been applied, pressure relief must be provided, e.g. by direct drainage.

A close visual examination should be made to verify cleanliness and soundness. Any weak or suspect areas should be repaired.

Application Instructions

Priming/ Scratch Coating

Nitoflor SL3000 UT should be applied as a primer/scratch coat at a coverage rate of up to a nominal 1 mm thickness; actual coverage rate will depend on concrete surface texture and porosity. This scratch coat is designed to prime and seal the floor. Mix (see Application below) and spread evenly by trowel. The scratch coat should be allowed to cure for 12 - 48 hours at 20°C before applying the Nitoflor SL3000 UT. If the scratch coat has been allowed to cure for >48 hours then the coat must be thoroughly abraded and a fresh layer of scratch coat applied.

If severe pin-holing is evident in the cured scratch coat, indicating that air is rising from the substrate, then remedial action should be taken. Contact your local Fosroc office for advice. Failure to do so may result in increased risk of pin-holing of the surface topping.

Application of Nitoflor SL3000 UT Topping

Fosroc Nitoflor SL3000 UT is a three-component product. A forced-action rotary paddle mixer is recommended for mixing the product. Shake the base component for 30 seconds prior to use. Drain the contents of the liquid base and liquid hardener components into a large plastic container and mix briefly. Load the coloured filler

component whilst mixing, and continue mixing for at least 1 minute, until a lump-free mix is obtained, including a scrape down if necessary.

Immediately discharge and spread the mix over the application area, using a notched trowel to achieve the required coverage rate. De-aerate using a spiked roller. Spike rolling should be carried out within 10 minutes of application in order to avoid interfering with flow and surface finish. Ensure that anchorage grooves are fully wetted out with material. Do not return to spike roll older applied areas as the product is fast-setting and this action will leave spoiling marks on the applied floor.

The finished floor should be protected from other trades using Kraft paper or similar breathable material. Polythene should not be used. Protect the installed floor from damp, condensation and water for at least 4 days.

Supply

Nitoflor SL3000 UT	20.25 kg packs
--------------------	----------------

Comprises:

Nitoflor SL3000 UT Part A	3 kg
Nitoflor SL3000 UT Part B	3 kg
Nitoflor SL3000 UT Filler	14.25 kg

Coverage

Nitoflor SL3000 UT (primer/scratch coat) floor	Coverage appropriate to texture and porosity of floor
--	---

Nominal 10 m²/pack

Nitoflor SL3000 UT (floor topping)	3.5 m ² /pack at 3 mm 2.5 m ² /pack at 4 mm 1.7 m ² /pack at 6 mm
------------------------------------	--

Note: Coverage figures given are theoretical. Actual site practical coverage figures may vary, due to wastage factors and the type and condition of the substrate.

Cleaning

Regular cleaning is essential to maintain and enhance the life expectancy, slip resistance and appearance of the floor. Fosroc Nitoflor SL3000 UT can be easily cleaned using industry standard cleaning chemicals and techniques. Consult your cleaning chemical and equipment supplier for more information.



Fosroc Nitoflor SL3000 UT

Health and Safety

Fosroc Nitoflor SL3000 UT should not come into contact with the skin and eyes, or be swallowed. Ensure adequate ventilation and avoid inhalation of vapours.

Wear suitable protective clothing, gloves and eye protection. If working in confined areas, suitable respiratory protective equipment must be used. The use of barrier creams provides additional skin protection. In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent.

In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. If swallowed seek medical attention immediately - do not induce vomiting. Refer to Product Safety Data Sheet for further information.

Rage, Mixing & Application

Fosroc Nitoflor SL3000 UT has a shelf life of 12 months (6 months for the filler component) if stored off the ground in dry store at 10 -30°C. Storage outside this temperature range or repeated fluctuations in storage temperature can reduce the storage life. Protect from frost.

Fire

Fosroc Nitoflor SL3000 UT is non-flammable.

Limitations

Do not proceed with application if atmospheric relative humidity is, or is anticipated to be within the tack-free period, >75% or if the surface temperature is <5°C above the dew point. Application should not commence when the substrate temperature or the ambient temperature is, or is anticipated to be, <10°C during the application or within the tack-free period.

The design strength of concrete surfaces must be a minimum of 25MPa compressive strength at 28 days.

The manufacture of Fosroc Nitoflor SL3000 UT is a batch process and despite close manufacturing tolerances, colour variation may occur between batches.

Slip resistance can reduce over time due to poor maintenance, general wear or surface contaminants. Nitoflor SL3000 UT has a smooth finish so can be expected to become slippery when wet. Good housekeeping practices must be observed.

Application can take place outside the ideal temperature range of 15 - 30°C, subject to a minimum of 10°C and a maximum of 34°C, however the surface finish may be subject to e.g. trowel and/or spike roller marks.

Fosroc Nitoflor SL3000 UT is not colour fast and may yellow over time. The rate of change will depend on UV light and heat levels and cannot be predicted. This will be more pronounced with lighter

colours and blue shades and does not compromise the product's in-service performance or chemical resistance characteristics.

The information contained in this document, and all further technical advice given, is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights.

In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

Some staining or discolouration may occur with some chemicals, depending on dwell time, temperature, type of chemical and degree of housekeeping employed. This does not necessarily affect the product service integrity or durability.

Technical Advice

For further information on this or any other Fosroc product, please contact your local Fosroc.



Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Service. **All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the recent version.**

Head Office

telephone: (+9714) 2039699

fax: (+9714) 2859649

email: agf@fosroc.com

Regional offices

Abu Dhabi, Al Gurg Fosroc
Bahrain, YBA Kanoo
Kuwait, Boodai
Oman, Al Amana

telephone: 673 1779
telephone: 17732820
telephone: 4817618
telephone: 24815080

fax: 673 1449
fax: 17732828
fax: 4832124
fax: 2481755

email: abudhabi@fosroc.com
email: bahrain@fosroc.com
email: kuwait@fosroc.com
email: oman@fosroc.com

Post Box 657, Dubai
United Arab Emirates
www.fosroc.com

