

Heavy duty self adhesive cross laminated bituminous waterproofing membrane

Uses

To provide a continuously bonded heavy duty waterproof membrane for building and civil engineering structures.

Advantages

- 2 mm & 3.0 mm thick (Nominal).
- Cold applied.
- Fast application.
- Uniform thickness of polymer bitumen membrane.
- Good adhesion to primed concrete substrates.
- Produces a continuous waterproof membrane system.
- Cross laminated film for superior performance

Description

Proofex 12 is a cold applied self-adhesive sheet membrane comprising of a polymer modified bitumen layer internally reinforced with polyester, bonded on to an outer surface of polyethylene film.

The polymer bitumen adhesive layer is protected on the underside by a silicone release paper which is removed just prior to the application of Proofex 12 to the tack coat primed substrate.

The applied membrane is then immediately protected from UV light and from mechanical damage during subsequent back filling by the application of Protection Board, or a sand/cement screed.

Specification

The waterproofing membrane shall be a 2 mm & 3.0 mm thick self adhesive sheet membrane comprising of a polymer modified bitumen layer internally reinforced with polyester, bonded on to an outer surface of polyethylene film. The polymer modified bitumen shall have an elongation in excess of 800% when tested in accordance with ASTM D412.

Technical support

Fosroc offers a comprehensive technical support service to specifiers, end users and contractors. It is also able to offer on-site technical assistance, an AutoCAD facility and dedicated specification assistance in locations all over the world.

Properties

Tensile strength (UEAtc)	: Long	500 N/5cm
	Trans	350 N/5cm
Elongation of membrane (UEAtc)	: Long	50%
	Trans	40%
Elongation of compound (ASTM D412)	: >	800%
Tear resistance (UEAtc)	: Long	>240N
	Trans	>200N
Adhesion to primed concrete (ASTM D1000)	: 2.0	N/mm
Adhesion to self (ASTM D1000)	: 2.0	N/mm
Chemical resistance (ASTMC543)	: Conforms	

Instructions for use

Surface preparation

Concrete surfaces should be float finished and free from cavities and projecting nibs. All surfaces shall be dry and free from frost, surface laitence and contamination.

Priming

Proofex Tack Coat or Proofex Tack Coat WB must be applied to the substrate and allowed to dry until it is tack free, prior to the application of the membrane. All surfaces must be re-primed if left for more than 24 hours prior to the application of Proofex 12. The use of Proofex Tack Coat WB is encouraged since it is water based.

Application

Smooth transition should be made at wall/floor slab junctions using a sand/cement mortar and internal and external corners at walls and upstands pre-protected with Proofex Corner Pieces prior to the application of the membrane.

The membrane should be applied to the substrate having first removed the siliconised release paper, pressing the polyethylene film firmly ensuring that the adhesive bitumen compound bonds continuously to the substrate with no air pockets.

Allow at least a 75mm edge and a 150mm end lap. All laps should be rolled firmly to achieve a good seal. End laps should be staggered.

On vertical or inclined surfaces, the membrane shall be laid from the lowest level upwards.

The membrane should be protected immediately after application in accordance with BS 8102:1990 by using Protection Board*†, or as appropriate with a sand/cement screed.

Fosroc Proofex 12

Proofex 12 and Proofex Engage

When used in conjunction with the Proofex Engage** heavy duty waterproofing system, vertical surfaces are to be protected with two layers of Proofex 12 and Protection Board**. The local Fosroc office will provide drawings for the joining detail between Proofex 12 and Proofex Engage**.

Limitations

Application temperature range: 5°C - 50°C.

For application below 15°C it may be necessary to slightly warm the back of the membrane to achieve an immediate bond. In cold conditions the membrane should be stored at temperatures above 20°C prior to application to facilitate ease of application and immediate bond to the substrate.

Estimating

Supply

Proofex 12	:	15m long x 1m wide roll
Proofex Tack Coat	:	20 and 200 litre drums
Proofex Tack Coat WB	:	20 and 200 litre drums

Coverage

Proofex Tack Coat	:	3-6m ² per litre
Proofex Tack Coat WB	:	3-6m ² per litre

Storage

All products have a shelf life of 12 months if stored in a cool, dry store, away from sources of heat, in the original unopened packing. It should be stored horizontally, not more than one pallet high.

Precautions

Health and safety

There are no health hazards associated with the use of Proofex 12.

If Proofex Tack Coat or Proofex Tack Coat WB is swallowed, **do not** induce vomiting - drink a glass of water. If contact with eyes occurs, flood with copious amounts of clean water for at least 15 minutes and seek medical advice. If on the skin, remove any contaminated clothing and wash skin thoroughly.

For further information, please consult Material Safety Data Sheets for the above products.

Fire

Proofex Tack Coat contains volatile, flammable solvents. Do not smoke in the presence of these products. Use in ventilated areas, well away from any ignition source.

Flash points

Proofex Tack Coat	:	> 38°C
--------------------------	---	--------

* Denotes the trademark of Fosroc International Limited

† See separate data sheet



Al Gurg Fosroc LLC

Post Box 657, Dubai
United Arab Emirates

www.fosroc.com

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Service. **All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the latest version.**

Head Office

telephone: (+9714) 2039699

fax: (+9714) 2859649

email: agf@fosroc.com

Regional offices

Abu Dhabi, Al Gurg Fosroc
Bahrain, YBA Kanoo
Kuwait, Boodai
Oman, Al Amana

telephone: 673 1779
telephone: 17738200
telephone: 4817618
telephone: 24815080

fax: 673 1449
fax: 17732828
fax: 4832124
fax: 24817554

email: abudhabi@fosroc.com
email: bahrain@fosroc.com
email: kuwait@fosroc.com
email: oman@fosroc.com

