

Nitocote® ET550

Epoxy tar based high performance resin coating

Uses

Nitocote ET550 provides protection to concrete and metal structures against corrosion from aggressive environments. Suitable for tanks above ground or in totally submerged conditions such as pipelinings. Particularly useful in sewage works, effluent plants and dock and harbour installations.

- High film build in single application
- Easily applied by brush or spray
- Provides long term corrosion protection
- No priming necessary in most cases
- Chemical and abrasion resistant
- Economic and versatile product

Description

Thixotropic pitch extended epoxy amine adduct formulation containing reinforcing inert fillers and special blend of solvents.

The product is supplied as a two-component system comprising a special blend of epoxy resins and a separate low viscosity amine hardener

Technical support

Fosroc offers technical support service to specifiers, end-users and contractors, as well as on-site technical assistance in locations all over the country.

Design Criteria

Nitocote ET550 is designed to be applied in two coats to achieve a minimum total dry film thickness of 350 microns. To achieve the correct protective properties, Nitocote ET550 must be applied at the coverage rates given overleaf

Properties

| |
|--|
| Specific gravity 1.38 - 1.40 |
| Volume Solids Mixed 66% (approx) |
| Dry film thickness (DFT) 350 microns |
| Wet film thickness(WFT) 530 micr/mm ² |

Note : In very hot or very cold conditions lower application-thickness is advised to avoid solvent entrapment. Recommended dft can be obtained in one coat by airless spray. Other methods will give lower film build.

| | | |
|-----------------|--|---------------|
| Number of coats | 1 - 3 depending on application conditions and method. phuric | |
| Pot life | at 20°C | 35°C |
| | 4 hours | 1 hour 30 min |

| | | |
|-------------|----------|----------|
| Drying Time | | |
| Touch dry | 4 hours | 2 hours |
| Fully dry | 7 days | 4 days |
| Recoatable | 24 hours | 18 hours |

| | | |
|-------------------------|--|--|
| Application temperature | 20°C - 40°C. Outside this temperature - consult Fosroc for guidance. | |
|-------------------------|--|--|

| | | |
|----------------------------------|---------------------------------------|--|
| Chemical resistance: | The fully cured coat is resisant to : | |
| Water | | |
| Sea water | | |
| Effluent water | | |
| Ground water | | |
| Sewage water | | |
| Distilled water | | |
| Atmospheric conditions | | |
| Exhaust and sewage gases | | |
| Dilute mineral acids and alkalis | | |
| Many organic solvents | | |
| Barnacles and organic growths | | |

Specification clauses

Corrosion, chemical and abrasion resistant

The chemical and abrasion resisant coating shall be Nitocote ET550, a high build, pitch extended epoxy amine adduct, two pack system, specifically designed to provide a tough, impermeable and corrosion resistant film.

Application Instructions

Surface preparation

Concrete

Surface should be clean, dry, free from laitance, loose particles and previous coatings. This should be achieved by blast cleaning, water jetting, wire brushing or grinding. Blow holes, if any, should be filled with a suitable putty like Nitomortar FC.

Steel

Any rust, millscale and other impurities should be removed from the substrate by blast cleaning to SA 2 1/2.

Nitocote® ET550

Hot dip galvanised steel

Galvanised steel should be lightly blast cleaned or cold phosphated. When the galvanised process includes quenching in an aqueous chromate solution, Nitocote ET550 can be applied directly to the substrate, provided it is clean and dry.

Mixing

Mix both components until a homogenous mixture is obtained. It is important that both components are intermixed thoroughly and that no traces of the components remain unmixed. If necessary adjust the viscosity by adding up to 5% Nitoflor Sol to the base component before mixing with hardener.

Application

Nitocote ET550 may be applied by brush or spray to give uniform finish. Faster rates of application are possible using airless spray equipment. A minimum nozzle pressure of 140 bar with an orifice size of 0.65 - 0.79mm has been found suitable. Upto 5% by volume Nitoflor Sol may be added to ease spray application.

Cleaning

Tools should be cleaned with Nitoflor Sol immediately after use.

Technical support

Fosroc offers a comprehensive technical support service to specifiers, end users and contractors. It is also able to offer on-site technical assistance, an AutoCAD facility and dedicated specification assistance in locations all over the world

Estimating

Packaging

Nitocote ET550 is supplied in 18L packs.
Nitoflor Sol - 5 and 20 litre jerry cans.

Coverage

Theoretical coverage : 1.80 - 1.90 m²/ litre for 350 microns DFT.
Practical coverage : Practical coverage may vary depending on substrate condition and application method.

Storage

Shelf life

6 months if stored at 30°C. Store in a cool dry place in unopened tins.

Precautions

Health and safety instructions

Some people are sensitive to epoxy resins, so gloves and a barrier cream should be used when handling these products. If contact with the resin occurs, it must be removed, before it hardens, with a resin removing cream followed by washing with soap and water. Solvent should not be used.

The use of goggles is recommended but should accidental eye contamination occur, it shall be washed thoroughly with plenty of water and medical treatment shall be sought immediately.

Ensure good ventilation and do not smoke during use

Fire

Nitocote ET550 and Nitoflor Sol are flammable. Do not smoke or use near naked flame.

Flash points

Nitocote ET550 Base 36°C

Nitocote ET550 Hardener 26°C

Nitoflor Sol 33°C

Additional information

Dekguard S was formerly known as Nitocote Dekguard S. Fosroc manufactures a wide range of products specifically designed for repair and refurbishment of damaged reinforced concrete. This includes hand-placed and spray grade repair mortars, fluid micro - concretes, chemical resistant epoxy mortars and a comprehensive package of protective coatings.

In addition, a wide range of complementary products is available. This includes joint sealants, water proofing membranes, grouting, anchoring and specialised flooring materials.

Nitocote® ET550

Fosroc have also produced several educational training videos which provide more detail about the mechanisms which cause corrosion within reinforced concrete structures and the solutions which are available to arrest or retard these destructive mechanisms. Further information is available from the publication : “ Concrete Repair and Protection - The Systematic Approach’.

For further information about products, training videos or publications, contact the local Fosroc office.



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

Embassy Point, No. 150,
2nd Floor, Infantry Road,
Bangalore 560 001,
Karnataka

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone

+91 80-42521900

fax

+91 80-22281510

e-mail

enquiryindia@fosroc.com

Regional Offices

Chennai

Hills Centre, Old No 5,
New No 9, 3rd Cross Street,
Jeth Nagar, Raja Annamalaipuram,
Chennai 600 028.
Ph: +91 44 61304500

Mumbai

MBC Park, 12th floor, Office No.12B,
'D' Block, Near G Corp/Hyper City
Kasarwadawali, Ghodbunder Road,
Thane (West) 400 615
Ph: +91 22 6229 6800
Fax: 022 62296809

Noida

Unit No. 601, Highway Tower-II
A-13/2, 6th Floor, Sector- 62
Gautam Buddha Nagar,
Noida 201 309, Uttar Pradesh
Ph: +91 120 6121900
Fax: 0120-4270622

Kolkata

304, Jodhpur Park
Kolkata 700 068
Ph: +91 33-65343188
Fax: 033-2499-0280